


UV cure type Solvent-free Adhesive


			SF-3201VG	
Material property	Viscosity	Pa · s	100	
Cured property (100mW/cm ² ,500mJ/cm ²)	UV cure rate	%	98	
	Volume shrinkage	%	3.6	
Adhesive properties (UV cured film)	Peel strength (180°)	Glass	N/25mm	30
		PC	N/25mm	17
		PMMA	N/25mm	17
		PP	N/25mm	20
Transparency (UV cured film)	Total light transmissivity	%	99.5	
	Haze	%	0.1	
	After hot water immersion (85°C,1000hr)	Total light transmissivity	%	99.7
	Haze	%	0.0	

(Typical Data)

【UV curability】 ※ Film thickness 100 μ m



【After hot water immersion (85°C,1000hr)】



Toray Fine Chemicals Co., Ltd.
www.torayfinechemicals.com

The information contained herein is, to the best of our knowledge and belief, accurate. However, since the conditions of handling and of use are beyond our control, we make no guarantee of results and assume no liability for damages incurred by following these suggestions. Nothing contained herein is to be construed as a recommendation for use in violation of any patents or of applicable laws or regulations.